

PVC BLANCO MATE - BOBINA

Formula_Base / Formulation / Grundrezeptur

FB90001

Color / Colour / Farbe

FC02801

Espesor / Thickness / Dicke

300 µm

Parámetro Parameter Parameter	Normativa Regulation Nomen	Método Methode Methode	Valores Values Werte		Unidades Units Einheiten
Tolerancia de Espesor Thicknesstolerance Dickentoleranz	EN 1849-2	Micrometer	300 +/- 5%		my
Resistencia a la Rotura Tensile stress at break Bruchspannung	EN ISO 527 - 3	70 mm/min	Longitudinal Longitudinal Längs	>42	MPa
			Transversal Transversal Quer	>39	
Alargamiento en la rotura Tensile strain at break Bruchdehnung	EN ISO 527 - 3	70 mm/min	Longitudinal Longitudinal Längs	>70	%
			Transversal Transversal Quer	>40	
Contracción Shrinkage Schrumpf	DIN 53377	10 min.; + 80 °C	< -5,0		%

CALIDAD

